

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-043730

(43)Date of publication of application : 23.02.1993

(51)Int.Cl.

C08J 9/00  
C08J 9/24  
C08L 27/18  
// C08F214/26  
(C08L 27/18  
C08L 27:12 )  
C08L 27:18

(21)Application number : 03-201778

(71)Applicant : HITACHI CABLE LTD

(22)Date of filing : 12.08.1991

(72)Inventor : SHIMIZU MASAZUMI

(54) PRODUCTION OF FLUORORESIN POROUS BODY

(57)Abstract:

PURPOSE: To remarkably improve compression creep resistance.

CONSTITUTION: In a method for producing a porous body of polytetrafluoroethylene (PTFE), a polymer blend prepared by replacing 10-1wt.% above-mentioned PTFE with a fluororesin composed of a copolymer (at 60-85mol% copolymerization ratio of dioxole) of tetrafluoroethylene and perfluoro(2,2-dimethyl-1,3-dioxole) or 50-5wt.% PTFE with a fluororesin composed of a 1:1 alternating copolymer of vinylidene fluoride and hexafluoroisobutylene is used.

## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's  
decision of rejection]

[Date of requesting appeal against examiner's  
decision of rejection]

[Date of extinction of right]